


## Super Nop® 52



### General Information

### Technical Data

Roll size	6'7" x 101'8" or 13'2" x 101'8"		
Overall Thickness	7/16" (+15% / -10%)		
Pile Thickness	3/8"		
Composition	100% solution dyed UV stabilized polypropylene fibers		
Pile Weight	52 ounces / square yard		
Overall Weight	93 ounces / square yard		
Backing	High density rubber		
Limited warranty	3 years		
<b>Performance</b>	<b>Certification</b>	<b>Standard</b>	<b>Result</b>
Range of Total VOCs	Green Label Plus	0.5 mg / m <sup>3</sup> or less	Pass/Certified
Surface Flammability	ASTM D2859 CPSC FF1-70	Uncharred area must be >1" in at least 7 of 8 specimens tested	Pass
Light Stability	AATC 16-04	Rating Key	5 – No Change
Static Electrical Propensity	ISO 6356	Antistatic: less than 2 kV	<2 kV
Sound Absorption	ISO 140-8	In decibels (dB)	29 dB
Thermal Resistance	DIN 52612	Maximum 0.15 m <sup>2</sup> K/W	0.09 m <sup>2</sup> K/W
<b>Adhesive</b>	<b>Moisture Limits</b>	<b>Application Method</b>	<b>Coverage</b>
MI 1000	MI 1000 Adhesive, 90% RH used "Dry-to-the-touch" over non-porous substrates. MI 1000 Adhesive, 95% RH used "Dry-to-the-touch" over porous concrete subfloors only.	1/32" x 1/16" x 1/32" U-notched trowel (FFA)	~ 150-175 ft <sup>2</sup> / gallon